Stickers International

www.stickersinternational.com

Technical Datasheet - Clear Labels

Polypropylene - Gloss Clear

Label material:
A clear bi-axially oriented, polypropylene film with a printreceptive topcoat.
Grammage: approx. 52 g/m² ISO 536
Caliper: approx. 57 µm ISO 534

Adhesive:
A general purpose permanent, acrylic based adhesive

Release liner:
A supercalandered siliconized white glassine paper. The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451)
Grammage: approx. 57 g/m² ISO 536
Caliper: approx. 49 µm ISO 534

Performance Data
Initial Tack: 10 N/25mm FTM 9 Glass
Peel Adhesion 90°: 6 N/25mm FTM 2 St.St.
Min. Application Temp.: 5 °C
Service Temperature: -20 °C to +80°C

Shelf Life:
To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

Polypropylene - Frosted Clear

Label material:
A clear, bi-axially oriented polypropylene film with a printreceptive matt topcoat.
Thickness: 59 micron ± 5%
Basic weight: 54 gsm ±5%

Adhesive:
A general purpose permanent, acrylic based adhesive. S692N is a clear permanent adhesive featuring excellent UV resistance and weatherability together with good adhesion performance, even on apolar substrates
Initial Tack: Good
Final adhesion: Good
Minimum application temperature: +5°C
Temp Range: -20°C to +80°C
UV Resistance: Excellent

Release liner:
BG40 white, a supercalendered glassine paper. The liner is made from FSC® certified paper (FSC Mix Credit, chain-ofcustody number: CU-COC-807907, Licence Code: FSC-C004451)
Thickness: 53 micron ±5%
Basic Weight: 59 gsm ±5%

Shelf life:
2 years when stored at 22* C / 50% RH